



Steel wire rope 6x7-WSC (7x7)



Warning: Not to be used for lifting purposes

Fill factor: 0,55

General use



Part code	Rope diameter mm	Tensile strength N/mm²	Finish	Rope lay	Min. breaking force kN	Steel area mm²	Lubrication	Weight kg/100m
101100104270040	1	1,960	Galvanized	sZ	0.76	0.43	Dry	0.38
101100154270040	1.5	1,960	Galvanized	sZ	1.71	0.97	Dry	0.86
101100204270040	2	1,960	Galvanized	sZ	3.04	1.73	Dry	1.54
101100254270040	2.5	1,960	Galvanized	sZ	4.75	2.7	Dry	2.4
101100304270040	3	1,960	Galvanized	sZ	6.84	3.89	Dry	3.46